## **Applied Rubber Linings Ltd**

## **Process Plant Liners**



## Technical Data Sheet

Material Reference

:

ARL/68 AS

Rubber.

Antistatic and Abrasion Resistant Soft Natural

Description & Application

FOR SPECIFIC APPLICATIONS PLEASE CONTACT APPLIED RUBBER LININGS LIMITED.

ARL/68 AS is a highly abrasive resistant soft natural rubber plant lining material, specifically formulated to be amtistath good resistance to many acids and chemicals.

Temperature Range

-35oC to 80oC (Depending upon conditions

and applications).

Specific Gravity

1. 15

Hardness

650 + 50 SHORE 'A'

Tensile Strength

19.2 MPa

Elongation At Break

315%

Compression Set

17.8%

Electrical Resistivity

N/A.

Health & Safety

See COSSH assessments

Typical Applications

Particularly useful for lining shot blasting equipment (reclaimers etc) where the build up of static can damage

Tel: 01452 381849

the rubber lining.

NOTE:-

INFORMATION GIVEN IN GOOD FAITH BUT DETAILS MAY

CHANGE WITHOUT PRIOR NOTIFICATION. CUSTOMERS SHOULD MAKE THEIR OWN ASSESSMENTS TO DETERMINE THAT THE MATERIALS ARE SUITABLE FOR SPECIFIC APPLICATIONS

www.applied-rubber.co.uk